

High-gloss varnish (clear coat)

FEATURES

CLEAR COAT is a high-gloss, traditional varnish for all wood surfaces above the waterline. The varnish is suitable for both interior and exterior surfaces. It is permanently elastic, weather-resistant, and UV-stable, providing long-lasting protection in marine environments. It ensures long-lasting high gloss and protects the wood from fading and yellowing. The fast drying allows for short recoating intervals. The good flow and application properties ensure easy and straightforward processing.

APPLICATION

- High-gloss varnish
- Suitable for all wood surfaces above the waterline

PRODUCT DATA

- Content: 0.75 l
- Color: Transparent, high gloss
- Specific gravity: Approx. 0.9 kg/l
- Thinning and cleaning of tools: YC COATING THINNER
- Coverage: Approx. 12.0 m²/Liter

PROCESSING

The substrate must be thoroughly clean, dry, and free of grease. Old coatings must be intact and well-adhered. If necessary, sand the old coating and carefully remove the sanding dust. CLEAR COAT can be processed in dry weather and at temperatures between +10°C and +30°C.

The varnish is applied with a brush or foam roller. For a new build, 5-6 layers are recommended for sufficient film thickness and the associated protection. On raw wood, the first two coats are thinned with 20% and 10% COATING THINNER, respectively. The following 2-3 coats are applied undiluted.

On already varnished wood, 1-2 renewal coats are applied. If necessary, the flow properties can be improved by adding a maximum of 5% COATING THINNER.

The recoating interval with itself is at least 4 hours, with a maximum waiting time of 2 days (at 20°C). If this interval is exceeded, the substrate must be re-sanded before continuing work.

PRECAUTIONS

For information on handling the products and disposal, please refer to the valid safety data sheet and the relevant leaflets of the professional association of the chemical industry. The above information, particularly the suggestions for processing and using our products, is based on our knowledge and experience under normal circumstances. Due to the different materials, substrates, and varying working conditions, no guarantee for a work result or liability, regardless of the legal relationship, can be derived from these instructions, nor from verbal advice, unless we are held liable for intent or gross negligence. The user must prove that they have provided us with all necessary knowledge, which is essential for proper and successful evaluation, in writing and in time. The rights of third parties must be observed. Our respective sales and delivery conditions apply. The latest technical data sheet, which can be requested from us, applies.

Copyright VOSSCHEMIE
www.yachtcare.de
November 2014-1